

Hong Kong Government Recognized Service Supplier
Approved Laboratory of The Woolmark Company

Members of:
American National Standards Institute
American Society for Testing and Materials
British Standards Institute

Hong Kong Association of Certification Laboratories
Hong Kong Toys Council

TEST REPORT

NUMBER: TJ00712534

TESTS CONDUCTED (AS REQUESTED BY THE APPLICANT)

1 FLAMMABILITY TEST (FTMS 191 METHOD 5903-1978):

TEST METHOD

THE APPARATUS AND METHODS OF TESTING WERE THOSE DESCRIBED IN FEDERAL TEST
METHOD STANDARD NO. 191 METHOD 5903-1978:

TEST RESULT :

<u>DAMAGE LENGTH</u>	
<u>WARP</u>	<u>FILLING</u>
(INCHES)	(INCHES)
4	4-1/2
5-1/8	5-1/4
4	5
6-1/8	5-1/8
5-7/8	4-1/8

AVERAGE :

5

<u>AFTERFLAME TIME</u>	
<u>WARP</u>	<u>FILLING</u>
NIL	NIL
NIL	NIL
NIL	NIL
NIL	NIL
NIL	NIL

AVERAGE :

NIL

<u>AFTERGLOW TIME</u>	
<u>WARP</u>	<u>FILLING</u>
NIL	NIL
NIL	NIL
NIL	NIL
NIL	NIL
NIL	NIL

AVERAGE :

NIL

REMARK : NIL - DID NOT IGNITE, NO FLAME SPREAD TIME WAS RECORDED.
THE FABRIC WEIGHT OF THE SAMPLE IS 2.1 OZ/YD².